




CEWELD Ni-Rod 44 Tig

TYPE	Tig rods for cast iron welding		
ANWENDUNGEN	Ductile, grey and malleable Cast Iron and Cast Steel repairs, rebuilding wornout parts and also suitable for joining steel t cast Iron.		
EIGENSCHAFTEN	Very low thermal expansion therefore good crack resistance in the weldmetal		
KLASSIFIKATION	AWS EN ISO	A 5.15: E NiFeMn-Cl 1071: NiFeMn-Cl	
GEEIGNET FÜR	Cast iron, Cast steel		

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)

C	Si	Mn	S	Ni	Cu	Al
0.25	0.15	11.9	0.002	42	0.04	0.003

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		690	35	190 HB

RÜCKTROCKNUNG

Not required

GAS ACC. EN ISO 14175

I1