

CEWELD Alloy 230

TYPE Nickel based Mig filler metal for welding similar NiCrW alloys.

ANWENDUNGEN In the chemical process industry, CEWELD® Alloy 230 is used for catalyst grid supports in ammonia burners, high-strength thermocouple protection tubes, high-temperature heat exchangers, ducts, high-temperature bellows, and various other key process internals. In the industrial heating industry, applications for 230 alloy include furnace retorts, chains and fixtures, burner flame shrouds, recuperator internals, dampers, nitriding furnace internals, heat-treating baskets, grates, trays, sparger tubes, thermocouple protection tubes, cyclone internals, and many more.

EIGENSCHAFTEN CEWELD® Alloy 230 combines properties which make it ideally suited for a wide variety of component applications in the aerospace and power industries. It is used for combustion cans, transition ducts, flame holders, thermocouple sheaths, and other important gas turbine components.

KLASSIFIKATION

AWS	A 5.14: ERNiCrWMo-1
EN ISO	18274: S Ni 6231(NiCr22W14Mo2)
W.Nr.	2.4733
F-nr	43
FM	6

GEEIGNET FÜR **UNS-Nummer: N06230**
Haynes Alloy 230,
ASTM: B435, B564, B572, B619, B622, B626, B366, 5981
AMS: 5878, 5839
Haynes 25 alloy

ZULASSUNGEN CE

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	Cr	Ni	Mo	W	Co	Al
	0.1	0.4	0.5	22	57	2	14	4	0.3

MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded	490	780	45	HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1