



CEWELD CuMn13Al7

TYPE CuMnAlNi (W.Nr: 2.1367) Mig/Mag welding wire.

ANWENDUNGEN Joint welds or building up of aluminum bronze. Cladding components undergoing metal to metal wear under high pressure. Especially suited for marine environments. The addition of manganese and nickel improves hardness and strength. Excellently suitable for joining and cladding of copper alloys, unalloyed and low-alloy steels and grey cast iron.

EIGENSCHAFTEN Highest grade of the Al-Bronze-types. Seawater-resistant copper-aluminum alloy without Zn with high toughness and improved hardness. "Very good weldability compare to the more common Al. bronzes. "

KLASSIFIKATION

AWS	A 5.7: ER CuMnNiAl
EN ISO	24373: Cu 6338 / CuMn13Al8Fe3Ni2
W.Nr.	2.1367
F-nr	37

GEEIGNET FÜR Ship propellers, copper, brass, pumps, seawater, desalting equipment, marine, pulling tools, shafts, guide grooves, sliding surfaces, cast iron, pully, UNS : C62300 - C63000, DIN : CuAl10Fe3Mn2 - CuAl10Ni5Fe4 - G-CuAl10Fe, Mat n° : 2.0936 - 2.0966 - 2.0940, CuNiAl, superstone etc..

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)

Si	Mn	Fe	Cu	Zn	Pb	Al	Ni+Co
0.05	13	3	Rem.	0.1	0.01	8	2.5

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		880	10	290 HB

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD CuMn13Al7

CUMN13AL7 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409317
BS-300	15	8720663409324

CUMN13AL7 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409362

CUMN13AL7 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409386