CEWELD CuAl9Fe

certilas® THE FILLER METAL SPECIALIST

TYPE

Copper-aluminium welding wire for Mig / Tig

ANWENDUNGEN

Joint welds or building up of aluminum bronze. Cladding components undergoing metal to metal wear. Joining steel to copper alloys, cast iron and or bronze.

EIGENSCHAFTEN

Special alloyed copper wire for Mig and Tig welding. The weld metal is a Cu-Al bronze. Sound, pore free deposits.

KLASSIFIKATION

AWS	A 5.7: ERCuAl-A2
EN ISO	24373: Cu 6180 / CuAl10Fe
W.Nr.	2.0937
F-nr	36

GEEIGNET FÜR

Suitable for seawater resistant applications. Joining steel to copper alloys, cast iron and or bronze. Excellent for metal spraying. Ship propellers, shipbuilding, pump building, shafts, guide grooves etc, UNS : C 60600 - C 61600 - C 68700, DIN : Cu Al5 - Cu Al8 - CuZn20Al2, Werkstoff Nr : 2.0916 - 2.0920 - 2.0960

ZULASSUNGEN

SCHWEISSPOSITIONEN

TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)

Si	Fe	Cu	Zn	Pb	Al
0.05	1	Rem.	0.01	0.01	10

MECHANISCHE GÜTEWERTE

Heat Treatment	$R_{P0,2}$ (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded		500	35	95	140 HB

RÜCKTROCKNUNG

Not required

GAS ACC. EN ISO 14175

I1, I3

CEWELD CuAl9Fe

CUAL9FE 1,0MM

Packaging	KG/unit	EanCode
D-300	15	8720663408846

CUAL9FE 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408853

CUAL9FE 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408860