



CEWELD CuSn12 Tig

TYPE Tin bronze alloy with high percentage of tin for virtually all welding procedures

ANWENDUNGEN Boilers and tubes out of copper or copper alloys, oven soldering etc.

EIGENSCHAFTEN Very good deoxidization and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn-Alloys. Widely used and recommended for oven soldering. High quality alloyed copper wire. Sound, pore free deposits and good electrical conductivity. Excellent corrosion resistance

KLASSIFIKATION EN ISO 24373: Cu 5410 / CuSn12P
W.Nr. 2.1056

GEEIGNET FÜR Tin bronze alloy with high percentage of tin for virtually all welding procedures. Very good deoxidisation and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn-alloys. Widely used and recommended for oven soldering.
Mat.n: 2.1016, 2.1020, 2.1030, 2.1050, 2.1052, 2.1056, 2.1080, 2.1086, 2.1090
CuSn8, CuSn7, CuSn6, CuSn4, G-CuSn10

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)

P	Cu	Zn	Pb	Sn
0.25	Rem.	0.03	0.01	12

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		350		120 HB

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1



CEWELD CuSn12 Tig

CUSN12 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422835
CUSN12 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422842
CUSN12 TIG 3,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422859
CUSN12 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422866