



CEWELD CuAl8 Tig

TYPE	Copper aluminium alloy for Tig welding and brazing					
ANWENDUNGEN	Rebuilding brass ship propellers and cladding surfaces against wear and corrosion attack. Welding galvanized plates or stainless steel sheets and suitable for cladding cast iron and un- and low alloyed steels.					
EIGENSCHAFTEN	High quality alloyed copper wire for the Tig process (Tig brazing as well). The weld metal is a Copper-Aluminum bronze. Sound, pore free deposits on ferrous and non-ferrous base materials. Excellent corrosion resistance					
KLASSIFIKATION	AWS EN ISO W.Nr. F-nr	A 5.7: ERCuAl-A1 24373: Cu 6100 / CuAl7 2.0921 36				
GEEIGNET FÜR	Brass, copper, steel, CuZn alloys, Ship propeller, AISI 304, sliding Surface, shafts, bearings etc.					
ZULASSUNGEN						
SCHWEISSPOSITIONEN	      					
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	Si 0.08	Mn 0.3	Cu Rem.	Zn 0.1	Pb 0.01	Al 7
MECHANISCHE GÜTEWERTE	Heat Treatment As Welded	R _{P0,2} (MPa)	R _m (MPa) 430	A5 (%) 40	Impact Energy (J) ISO-V RT 100	Hardness 100 HB
RÜCKTROCKNUNG	Not required					
GAS ACC. EN ISO 14175	I1, I3					



CEWELD CuAl8 Tig

CUAL8 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663422873

CUAL8 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663422880

CUAL8 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663422897

CUAL8 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663422903

CUAL8 TIG 4,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663422910