



CEWELD AA M CrMo1V

TYPE	Nahtloser Metallpulverfülldraht für M21 Schutzgas. (Typ CrMo1V, 1.7745)								
ANWENDUNGEN	CEWELD® AA MCrMo1V ist ein Metallpulverfülldraht mit hervorragender Schweißbadhandhabung. Die Hauptanwendungsbereiche sind: Gießereien, Fertigungsschweißen								
EIGENSCHAFTEN	CEWELD® AA MCrMo1V zeigt geringer Spritzerverlust, extrem rissbeständig. Geeignet zum wirtschaftlichen Schweißen von CrMoV-Stählen bis 550 °C. Durch den nahtlosen Herstellungsprozess liegt der Wasserstoffgehalt auch nach längerer Lagerung unter 3 ml/100 g Schweißgut. Gute Spaltüberbrückbarkeit. Im Strombereich (PF) von 85 - 175 A für vertikale Steignähte geeignet.								
KLASSIFIKATION	AWS	A 5.28: ER80T15-GM2M H4, A 5.36: E80T15-M21PY-G-H4							
	EN ISO	17634-A: T Z M M 1 H5							
	W.Nr.	~1.7745							
	F-nr	6							
	FM	4							
GEEIGNET FÜR	1%Cr 0,5%Mo, ISO 15608: ~5,1 (0,75 % < Cr < 1,5 % und Mo < 0,7 % und ~0,3% V) 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4, G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12								
ZULASSUNGEN									
SCHWEISSPOSITIONEN	     								
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Mo	V
	0.1	0.3	0.9	0.015	0.015	1.1	0.3	1	0.25
MECHANISCHE GÜTEWERTE	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness	
	690°C±15°C 6h		550	700	20	RT		HRc	
RÜCKTROCKNUNG	Nicht erforderlich								
Heat Treatment: Quenched and tempered (30 min at 950° C / oil and 16 h at 700°C furnace cooling to 300° C) R _{p0,2} >440 MPa R _m 590-780 MPa A5 > 15 Quenched and tempered (30 min at 950° C / air and 16 h at 700°C furnace cooling to 300° C) R _{p0,2} >440 MPa R _m 590-780 MPa A5 > 15									
GAS ACC. EN ISO 14175	M21								