



CEWELD SG 2 Tig

TYPE	Copper coated welding rod for welding un and -low alloyed steels upto 420 MPa yield strength.(ER70S6, 3Si1)							
APPLICATIONS	CEWELD® SG2 Tig is a Tig-Rod for joining and surfacing unalloyed and low-alloy structural steels. Typical in Shipbuilding, piping, bridges, repair, construction, car-plate welding etc. Suitable for sour gas applications due to the very low P/S/Ni content							
PROPERTIES	CEWELD® SG2 Tig is extreme easy to weld with excellent welding properties. High world wide excepted quality with controlled cast en helix for semi and or semi-automatic applications.							
CLASSIFICATION	AWS	A 5.18: ER 70S-6						
	EN ISO	636-A: W 46 5 3Si1						
	W.Nr.	1.5125						
	F-nr	6						
	FM	1						
SUITABLE FOR	Rp< 420 MPa (60ksi) ISO 15608: 1.1(ReH < 275 MPa), 1.2 (275 < ReH < 360 MPa), 1.3 (ReH > 360 MPa < 420 MPa) 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0619, 1.1100, 1.0409, 1.0421, 1.0426, 1.0429, 1.0430, 1.0436, 1.0473, 1.0481, 1.0482, 1.0484, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.8902, 1.8912, 1.8932 10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6, S235JR-S355JR, S235JO-S355JO, P195TR1-P265TR1, P195GH-P265GH, L245NB-L360NB, L245MB-L360MB, L415NB, L415MB, WStE 380, WStE 420, S420NL A, B, D, E, A 32-E 36 ASTM A 105, A 106, Gr. A, B; A 283 Gr. A, C; A 285 Gr. A, B, C; A 501, Gr. B; A 573, Gr. 58, 65, 70; A 633, Gr. A, C; A 711 Gr. 1013; API 5 L Gr. B, X42, X52, X60 Domex 315-420MC,MC Plus, ML							
APPROVALS	TÜV: (19806), CE							
WELDING POSITIONS								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C		Si			Mn		
	0.08		0.85			1.45		
MECHANICAL PROPERTIES	Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness
					RT	-40°C	-50°C	
	As Welded	450	560	24	200	150	60	HRc
REDRYING	Not required							
GAS ACC. EN ISO 14175	I1							



CEWELD SG 2 Tig

SG 2 TIG 0,8 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411235

SG 2 TIG 1,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411242

SG 2 TIG 1,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411259

SG 2 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411266

SG 2 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411280

SG 2 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411297

SG 2 TIG 3,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411303

SG 2 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411310

SG 2 TIG 4,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411327

SG 2 TIG 5,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411334