



CEWELD OA 410 NiMo

TYPE	Self-Shielded fluxcored CrNiMo wire
APPLICATIONS	Bridge bearings, sealing surfaces, corrosion, slide ring sealing, centrifuge, continuous casting rolls
PROPERTIES	The corrosion resistant deposit with a medium hardness is resistant against impact wear as well as permanent stress by heat influence, metal wear and high surface pressure

CLASSIFICATION	AWS	A 5.22: E410NiMoT0-3
	EN ISO	14700: T Fe7

SUITABLE FOR	13%Cr - 4%Ni - 0,5%Mo Steel 1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414, GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13 ACI Gr. CA 6 NM
--------------	--

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	P	Cr	Ni	Mo	Fe
0.05	0.9	1	0.025	14	4.5	0.75	Rem.

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				40 HRc

REDRYING	140°C / 24 hr
----------	---------------

GAS ACC. EN ISO 14175



CEWELD OA 410 NiMo

OA 410 NIMO 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411808