



# CEWELD NiFe 60-40

TYPE	Welding wire for cast iron and dissimilar welding.																										
APPLICATIONS	CEWELD® NiFe 60-40 is ideal for welding mixed joints, for example, cast iron, high-alloy, stainless, and heat-resistant steels, as well as structural steels. It is also ideal for thick-walled workpieces and steels with low carbon content. Examples include housings for pumps and valves, frames, and machining errors on castings, crushers, and gearboxes.																										
PROPERTIES	CEWELD® NiFe 60-40 (~60% Ni, ~40% Fe) is a nickel-iron-based welding consumable. It has excellent weldability with extreme crack resistance and ductile weld metal. The color of the weld metal alloy is similar to that of the base material and corrodes in the same way. It has good welding and wetting properties as well as high resistance to porosity. It is very well suited for welding with robots or automated processes.																										
CLASSIFICATION	<table><tr><td>AWS</td><td>A 5.15: ER NiFe-CI</td></tr><tr><td>EN ISO</td><td>1071: SC NiFe-1</td></tr><tr><td>W.Nr.</td><td>2.4560</td></tr></table>									AWS	A 5.15: ER NiFe-CI	EN ISO	1071: SC NiFe-1	W.Nr.	2.4560												
AWS	A 5.15: ER NiFe-CI																										
EN ISO	1071: SC NiFe-1																										
W.Nr.	2.4560																										
SUITABLE FOR	<p><b>GG, GGG Spheroidal Cast Iron, Diluted Cast Iron, old Cast Iron, Steel to Cast Iron etc.</b></p> <p><b>Lamellar grey cast irons</b> EN-GJL-100 to EN-GJL-350</p> <p><b>Malleable cast irons</b> EN-GJMB-350-10 to 650-2</p> <p><b>Nodular cast irons</b> EN-GJS-400-15 to EN-GJS-800-2</p> <p><b>EN 1561:</b> EN-GJL-100, EN-GJL-150, EN-GJL-200, EN-GJL-250, EN-GJL-300, EN-GJL-350, GG10, GG15; GG20, GG25; GG30; GG35; GG40</p> <p><b>EN 1562:</b> EN-GJMB-350, EN-GJMB-550, EN-GJMW-350, EN-GJMW-550, GTS 35, GTS 55, GTW 35, GTW 55</p> <p><b>EN1563:</b> EN-GJS-400-15, EN-GJS-400-18, EN-GJS-450-10, EN-GJS-500-7, EN-GJS-600-3, EN-GJS-700-2. GGG40, GGG45, GGG50, GGG60; GGG70, GGG80</p> <p>X120Mn12, 1.3401</p>																										
APPROVALS	CE, DB: (62.206.01)																										
WELDING POSITIONS																											
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table><thead><tr><th>C</th><th>Si</th><th>Mn</th><th>P</th><th>S</th><th>Ni</th><th>Fe</th><th>Cu</th><th>Al</th></tr></thead><tbody><tr><td>0.05</td><td>0.15</td><td>0.8</td><td>0.001</td><td>0.001</td><td>58</td><td>Rem.</td><td>0.03</td><td>0.07</td></tr></tbody></table>									C	Si	Mn	P	S	Ni	Fe	Cu	Al	0.05	0.15	0.8	0.001	0.001	58	Rem.	0.03	0.07
C	Si	Mn	P	S	Ni	Fe	Cu	Al																			
0.05	0.15	0.8	0.001	0.001	58	Rem.	0.03	0.07																			
MECHANICAL PROPERTIES	<table><thead><tr><th>Heat Treatment</th><th>R<sub>P0,2</sub> (MPa)</th><th>R<sub>m</sub> (MPa)</th><th>A<sub>5</sub> (%)</th><th>Hardness</th></tr></thead><tbody><tr><td>As Welded</td><td>350</td><td>450</td><td>16</td><td>185 HB</td></tr></tbody></table>									Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded	350	450	16	185 HB								
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness																							
As Welded	350	450	16	185 HB																							
REDRYING	Not required																										
GAS ACC. EN ISO 14175	I1, M11, M12																										



# CEWELD NiFe 60-40

## NIFE 60-40 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663420725
Drum	250	8720663420749

## NIFE 60-40 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663420732