



CEWELD E AlSi 5

TYPE Stick welding electrode for SMAW welding of aluminum alloys.(E AlSi5, E 4043)

APPLICATIONS CEWELD® E AlSi 5 is for welding Aluminium alloys with maximum 2% alloying elements and for aluminium alloys containing up to 7% Si.Also excellent for joining dissimilar grades of aluminum. General applications: engine blocks, cylinder heads, tanks, containers, frames, lorry tipper.

PROPERTIES CEWELD® E AlSi 5 have a very good weldability with good penetration and porosity free deposit, Unique self lifting slag and improved coating against moisture pick up. (after anodizing the welding will appear as a dark grey color)
Start by using the upper portion of the amperage range. Feed the Electrode quickly and move fast maintaining a very close arc gap

CLASSIFICATION	AWS	A 5.3: E 4043
	EN ISO	18273: E AlSi5(A)
	W.Nr.	3.2245
	F-nr	23
	FM	23

SUITABLE FOR AlSi alloys with max. 7% Silicium, AlMg Alloys with max. 3% Magnesium,
Mat.n: 3.2151, 3.3206, 3.3210, 3.3211, 3.2305, 3.2315, 3.2341, 3.2371, 3.4335
AlMgSi 0.5, AlMgSi 0.7, AlMgSi 1, AlMg1SiCu, AlSi7Mg0,3, G.AlSi5Mg, G.AlSi6Cu4, AlMgSi,
AlZn4,5Mg1
Iso.n: 6060, 6005A, 6082, 6061, 4210, 4500, 6060, 7072

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


Si	Mn	Ti	Fe	Cu	Mg	Al
5	0.02	0.2	0.2	0.3	0.05	Rem.

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	100	150	14	60 HB

REDRYING 140°C / 1 hr

GAS ACC. EN ISO 14175



CEWELD E ALSi 5

E ALSI 5 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406712

E ALSI 5 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406729

E ALSI 5 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406736