



CEWELD CuSn Tig

TYPE	Copper welding wire alloyed with Sn for Tig welding
APPLICATIONS	Boilers and tubes out of copper or copper alloys, oven soldering etc.
PROPERTIES	• High quality alloyed copper wire • Sound, pore free deposits and good electrical conductivity • Excellent corrosion resistance
CLASSIFICATION	AWS EN ISO W.Nr. F-nr A 5.7: ERCu 24373: Cu 1898 / CuSn1 2.1006 31
SUITABLE FOR	Bronze alloy with minimally 0.8 tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Cu and copper- alloys. Widely used in oven soldering.

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

Si	Mn	P	Cu	Pb	Sn
0.4	0.4	0.1	99	0.01	0.5

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded		220		60 HB

REDRYING Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD CuSn Tig

CUSN TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408662

CUSN TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408679

CUSN TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408686

CUSN TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408693

CUSN TIG 4,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408709