



CEWELD AlSi 5 Tig

TYPE	Tig aluminium welding wire alloyed with silicon							
APPLICATIONS	Tig filler metal for welding Aluminium alloys with maximum 2% alloying elements and for aluminium alloys containing up to 7% Si.(after anodizing welding will be of a dark grey colour)							
PROPERTIES	Thanks to its excellent weldability and good penetration this alloy is used mainly in construction and automotive industry. The silicon addition results in improved fluidity (wetting action), making the alloy the preferred choice of welders. The alloy is not sensitive to weld cracking and produces bright, almost smut-free welds. Not recommended for anodizing. Non-heat treatable. Thicker sections should be preheated (150°C) prior to welding.							
CLASSIFICATION	AWS	A 5.10: ER4043						
	EN ISO	18273: S Al 4043A (AlSi5(A))						
	W.Nr.	3.2245						
	F-nr	23						
SUITABLE FOR	AlMgSi 0, AlSiMg (A), AlSi 1 MgMn, AlMg1SiCu, 3.3206, 3.3210, 3.2315, 3.3211, EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061, EN AC 45000,							
APPROVALS	CE							
WELDING POSITIONS	      							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Ti	Fe	Cu	Zn	Al	V
	5	0.1	0.01	0.11	0.03	0.01	Rem.	0.02
MECHANICAL PROPERTIES	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded		135	175	17	HRc		
REDRYING	Not required							
GAS ACC. EN ISO 14175	I1, I3							



CEWELD ALSi 5 Tig

ALSI 5 TIG 0,8 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663405432

ALSI 5 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407597

ALSI 5 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407603

ALSI 5 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407610

ALSI 5 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407627

ALSI 5 TIG 4,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407634

ALSI 5 TIG 5,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663407641