



CEWELD NiCro 52 Tig

TYPE	Solid nickel base welding wire for Tungsten Inert Gas (Tig) welding.								
APPLICATIONS	CEWELD Nicro 52 filler metal is used for welding nickel-chromium-iron (Inconel 690) alloys to themselves, and for dissimilar welding between nickel-chromium-iron alloys and steels or stainless steels. The applications include surfacing as well as clad-side welding. Interpass temperature of 150°C should be respected,								
PROPERTIES	Excellent resistance against oxidizing media combined with high mechanical strength at room temperature but also at extreme high temperatures combined with high ductility due to the high chromium content. Alloy 690 was developed to offer greater resistance to stress corrosion in the nuclear industry, pure water environment..								
CLASSIFICATION	AWS	A 5.14: ERNiCrFe-7							
	EN ISO	18274: S Ni 6052(NiCr30Fe9)							
	W.Nr.	2.4642							
	F-nr	43							
	FM	6							
SUITABLE FOR	Inconel 690, VDM Alloy 690, Nicrofer 6030 N, FM 52, 2.4642, NiCr29Fe								
APPROVALS									
WELDING POSITIONS	      								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Mo	Ti	Fe	Al
	0.02	0.4	0.8	30	60	0.2	0.5	10	0.3
MECHANICAL PROPERTIES	Heat Treatment			R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded			770	870	16	HRc		
	580°C±15°C 1h			260	580	30	200 HB		
REDRYING	Not required								
GAS ACC. EN ISO 14175	I1								



CEWELD NiCro 52 Tig

NICRO 52 TIG 1,6 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418241

NICRO 52 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418265