



CEWELD MA SS 2367

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools.				
APPLICATIONS	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures up to 550°C				
PROPRIÉTÉS	Abrasion combined with higher temperatures.				
CLASSIFICATION	EN ISO W.Nr.	14700: S Fe 13 1.2367			
CONVIENT POUR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.				
AGRÉMENTS					
POSITIONS DE SOUDAGE	      				
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C 0.2	Mn 0.6	Cr 6.2	Mo 3.2	Fe Rem.
PROPRIÉTÉS MÉCANIQUES	Heat Treatment As Welded	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 45 HRc
ETUVAGE	Not required				
GAS ACC. EN ISO 14175	M11				



CEWELD MA SS 2367

MA SS 2367 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401823