


CEWELD SG TITAN

TYPE	Special Mag wire with desoxidation additions for improved welding properties.						
APPLICATIONS	Recommended for applications that require high purity of the weld metal. Ideal for diluted, rusty, painted or galvanized steel plates in maintenance and repair. Car restoration, body shops, frames and overhaul work.						
PROPRIÉTÉS	Low spatter formation, excelent flowing and desoxidation properties due to the addition of Zr, Ti and Aluminium. SG Titan is a bronzed wire to offer excellent feeding properties with standard steel liners.						
CLASSIFICATION	AWS	A 5.18: ER 70S-2					
	EN ISO	14341-A: G 46 A M21 2Ti					
	F-nr	6					
	FM	1					
CONVIENT POUR	Rp< 460 MPa (70ksi) ISO 15608: 1.1 ReH ≤ 275 MPa, 1.2 275 < ReH ≤ 360 MPa , 1.3 ReH > 360 MPa, 2.1 360 < ReH ≤ 460 MPa 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0619, 1.1100, 1.0409, 1.0421, 1.0426, 1.0429, 1.0430, 1.0436, 1.0473, 1.0481, 1.0482, 1.0484, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.8902, 1.8912, 1.8932 S235JR-S355JR, S235JO-S355JO, P195TR1-P265TR1, P195GH-P265GH, L245NB-L360NB, L245MB-L360MB, L415NB, L415MB, WStE 380, WStE 420, S420NL A, B, D ASTM A 106, Gr. A, B; A 283 Gr. A, C; A 285 Gr. A, B, C; A 501, Gr. B; A 573, Gr. 58, 65, 70; A 633, Gr. A, C; A 711 Gr. 1013; API 5 L Gr. B, X42, X52, X60 5						
AGRÉMENTS	CE						
POSITIONS DE SOUDAGE	      						
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	P	S	Al	Ti+Zr
	0.05	0.5	1.2	0.01	0.01	0.1	0.17
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					-30°C		
	As Welded	460	565	24	60		HRc
ETUVAGE	Not required						
GAS ACC. EN ISO 14175	M21						



CEWELD SG TITAN

SG TITAN 0,6MM

Packaging	KG/unit	EanCode
D-200	5	8720663404930
D-300	15	8720663404947

SG TITAN 0,8MM

Packaging	KG/unit	EanCode
D-200	5	8720663405036
D-300	15	8720663405067

SG TITAN 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663405319
Drum	250	8720663405326

SG TITAN 1,2MM

Packaging	KG/unit	EanCode
D-300	15	8720663405333