


CEWELD Ni-Rod FM 99

TYPE	Solid Nickel based filler metal for MIG welding.						
APPLICATIONS	CEWELD Ni 99 FM 99 is developed for welding ductile, grey and malleable cast irons. Ni 99 can also be used for dissimilar welding between cast iron and low alloyed steel or carbon steels.						
PROPRIÉTÉS	This Nickel weld deposit offers a easily machinable weld deposit with high ductility and no undercut.						
CLASSIFICATION	AWS W.Nr.	A 5.15: E Ni-CI, 1071: SC Ni-CI UNS N02215					
CONVIENT POUR	Grey cast iron, malleable, nodular, dissimilar welding : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.						
AGRÉMENTS							
POSITIONS DE SOUDAGE							
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	S	Ni	Fe	Cu
	0.09	0.35	0.35	0.01	Rem.	0.4	0.2
PROPRIÉTÉS MÉCANIQUES	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness	
	As Welded		250	490	12	HRc	
ETUVAGE	Not required						
GAS ACC. EN ISO 14175	M11						



CEWELD Ni-Rod FM 99

NI-ROD FM 99 1,2MM

Packaging	KG/unit	EanCode
BS-300	13,6	8720663417688