



CEWELD E Alloy B3

TYPE	Nickel based stick electrode		
APPLICATIONS	Hastelloy B2, Hastelloy B3, dissimilar welding Hastelloy to nickel- of iron-based corrosion alloys, for weld overlay cladding		
PROPRIÉTÉS	E Alloy B3 is a nickel-base alloy with excellent resistance tot hydrochlorid acid at all concentrations and tempertures. It also withstands hydrogen chloride, sulfuric, acetic, hydrofluoric nd phosphoric acids. The alloy has improved thermal stability, fabricability and stress corrosion cracking resistance.		
CLASSIFICATION	AWS	A 5.11: E NiMo-10	
	EN ISO	14172: Ni1067 (NiMo30Cr)	
	W.Nr.	2.4695	
	F-nr	43	
CONVIENT POUR	Hastelloy B2, Hastelloy B3 oder B4, Nicrofer® 6629 NiMo29Cr, NiMo28 2.4600, 2.4617 UNS N 10629, N 10629, N10665 ASTM: B 333, B 335, B 564, B 619, B 622, B 626		

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)

C	Si	Mn	Cr	Ni	Mo	Fe	W	Co
0.01	0.1	1.5	2.5	68	27	1.2	1	1

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	400	700	40	120	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175



CEWELD E Alloy B3

E ALLOY B3 3,2 X 355MM

Packaging	KG/unit	EanCode
Can	2,27	8720663419897

E ALLOY B3 4,0 X 355MM

Packaging	KG/unit	EanCode
Can	2,27	8720663419927