




CEWELD CroNiMo Ti

TYPE	Rutile basic Stainless steel stick electrode for welding dissimilar joints.		
APPLICATIONS	Suitable for welding low-alloyed steel to stainless or austenitic manganese steels. Maintenance and repair welding of unknown or difficult to weld steels.		
PROPRIÉTÉS	Good corrosion resistance against seawater and general corrosion with excellent welding properties with self detaching slag.		
CLASSIFICATION	AWS	A 5.4: E 308Mo-16	
	EN ISO	3581-A: E 20 10 3 RB 32	
	W.Nr.	1.4431	
	F-nr	5	
	FM	5	
CONVIENT POUR	W.Nr: 1.4311, 1.4401, 1.4404, 1.4408, 1.4571, 1.4573, 1.4580,1.4581, 1.4712, 1.4742, 1.4828, X 12 CrNi 22 12, X5CrNiMo17-12-2, X2CrNiMo17-12-2, G-X5CrNiMo19-11-2, X6CrNiMoTi17-12-2, X10CrNiMoTi18-12, X6NiCrMoNb17-12-2, G-X5CrNiMoNb19-11-2 NFA 35-578 : Z 15 CN 24.13 ASTM/AISI : 304, 347, 309, 316, 316L, 316Ti, 316Cb UNS: S31600, S31603, J92900, S31635, S31640 UGINE : NS 24, R 27. A, UGINOX 17-10 M, UGINOX 18-11 ML, UGINOX 17-11 MT + for dissimilar joints between low alloy/mild steels and stainless steels.		

AGRÉMENTS CE

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL DE
SOUDURE (%)

C	Si	Mn	P	S	Cr	Ni	Mo	Fe
0.07	0.8	2	0.025	0.015	20	11	2.5	Rem.

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	420	600	35	70	HRc

ETUVAGE 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD CroNiMo Ti

CRONIMO TI 2,0 X 300MM

Packaging	KG/unit	EanCode
Can	2,4	8720663416391

CRONIMO TI 2,5 X 300MM

Packaging	KG/unit	EanCode
Can	2,2	8720663416407

CRONIMO TI 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,6	8720663416414

CRONIMO TI 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663416421

CRONIMO TI 5,0 X 450MM

Packaging	KG/unit	EanCode
Can	3,2	8720663416438