



CEWELD FL 830 ESHC

TYPE	High basic flux for stainless steel strip electro slag cladding.		
APPLICATIONS	Designed for ES strip cladding in offshore, apparatus, vessel, boilers and chemical industry.		
PROPRIÉTÉS	FL 830 ESHC is a highly basic flux for stainless steel strip electro slag cladding. Basicity: about 4,0 (according to Boniszewski) Current: DC + Grain size: 2-16		
CLASSIFICATION	EN ISO	14174: ES A FB 2B 5644 DC	
CONVIENT POUR	Electro slag (ESW) cladding with stainless steel strip, 308L, 309L, 316L, 2209 Duplex, 347, 309LNb, 309LMo. Alloy 59®, C276®		
AGRÉMENTS			
POSITIONS DE SOUDAGE	PAPBPC		
COMPOSITION CHIMIQUE TYPIQUE EN POIDS (%)	CaF2	SiO2	CaO+MgO
	70	20	5
PROPRIÉTÉS MÉCANIQUES			
ETUVAGE	Not required		
GAS ACC. EN ISO 14175			



CEWELD FL 830 ESHC

FL 830 ESHC 0,2 - 1,6MM

Packaging	KG/unit	EanCode
Bag	25	8720663404169