




CEWELD FL 160

TYPE	High basic SAW flux with low hydrogen content.			
APPLICATIONS	Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..			
PROPRIÉTÉS	FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20			
CLASSIFICATION	EN ISO	14174: SA FB 1 55 AC H5		
CONVIENT POUR	S355, S420, S460, X65, X70, X80			
AGRÉMENTS				
POSITIONS DE SOUDAGE				
COMPOSITION CHIMIQUE TYPIQUE EN POIDS (%)	Al2O3 20	CaF2 20	SiO2 15	CaO+MgO 40
PROPRIÉTÉS MÉCANIQUES				
ETUVAGE	Not required			
GAS ACC. EN ISO 14175				



CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015