



CEWELD Al 99,0 Tig

TYPE	99,0 % pure aluminum filler metal for Tig welding				
APPLICATIONS	Aluminum wire for welding mostly pure aluminum (maximum 0,95% of alloyed elements). Applications in chemistry, electronics, construction and food industries.				
PROPRIÉTÉS	This 99,0% pure aluminum filler metal offers excellent weldability and is the strongest in the 1000 series of the pure aluminium grades. Heavy parts and thicker plates should be preheated (150°C), prior to welding. At the same time, it keeps the benefits of being relatively lightly alloyed (compared to other series), such as high electrical conductivity, thermal conductivity, corrosion resistance, and workability. It can be strengthened by cold working, but not by heat treatment.				
CLASSIFICATION	AWS EN ISO F-nr	A 5.10: ER1100 18273: S Al 1100 (Al99,0Cu) 21			
CONVIENT POUR	Al99,0 Al.99,5 Al.99,7 E-Al., 99,5, 3.0205, 3.0255, 3.0275, 3.0257, EN AW 1200, EN AW 1050A, EN AW 1070A, EN AW 1350, 1060, 1070, 1080, and 3003.				
AGRÉMENTS	CE				
POSITIONS DE SOUDAGE					
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	Mn 0.03	Cu 0.1	Al 99.5	Si+Fe 0.75	
PROPRIÉTÉS MÉCANIQUES	Heat Treatment As Welded	R _{P0,2} (MPa) 52	R _m (MPa) 93	A5 (%) 30	Hardness HRc
ETUVAGE	Not required				
GAS ACC. EN ISO 14175	I1, I3				