



CEWELD AA R500SR

TYPE	Seamless copper coated rutile flux-cored wire for M21.					
APPLICATIONS	Offshore, Shipbuilding, pressure vessels, orbital pipe work.					
PROPRIÉTÉS	AA R500 SR is a seamless rutile cored wire and has excellent modelling ability, therefore excellent forced position welding in all positions at high amperage. Down to -60 °C very good impact values are achieved also with very good PWHT results. Particularly suitable for welding on ceramics in all positions. Low spatter losses, easily removable slag.					
CLASSIFICATION	AWS	A 5.29: E81T1-Ni1M-J H4, A 5.36: E81T1-M21A8-Ni1-H4				
	EN ISO	17632-A: T 50 6 1Ni P M21 1 H5				
CONVIENT POUR	ReH ≤ 500 MPa ISO 15608: 1.1, 1.3, 2.1, 2.2 (ReH max. 500 MPa), 3.1 (ReH max. 500 MPa) 1.0580 to 1.0070, 1.8900 to 1.8905, 1.8930 to 1.8935, 1.8910 to 1.8915, 1.6217, 1.6210, 1.0481, 1.0482, 1.0551, 1.0553. S275N-S460N, S275NL-S460NL, S275M-S460M, S275ML-S460ML, P355N, P355NH, P460N, P460NH, P275NL1-P460NL1, P275NL2- P460NL2, L360NB, L415NB, L360MB-L450MB, L360QB-L450QB ASTM A 203 Gr. D, E; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65, 70; A 572 Gr. 42, 50, 55, 60, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C; API 5 L X52, X60, X65, X52Q, X60Q, X65Q, X70Q Oceanfit 52, Oceanfit 60, Oceanfit 65, Oceanfit 355, Oceanfit 420, Oceanfit 460, alform plate 460M; durostat 400, 450, 500, durostat B2, aldur 500Q, aldur 500QL, aldur 500QL1, N-A-XTRA 56					
AGRÉMENTS	CE					
POSITIONS DE SOUDAGE	      					
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	P	S	Ni
	0.08	0.5	1.4	0.015	0.015	0.9
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
	As Welded	550	600	22	-60°C	HRc
	570°C- 620°C 1h	520	580	22	70	HRc
					50	HRc
ETUVAGE	Not required					
GAS ACC. EN ISO 14175	M21					



CEWELD AA R500SR

AA R500SR 1,2MM

Packaging	KG/unit	EanCode
BS-300	16	8720663424563