



CEWELD SACW CrMo1V

TYPE	High- basicity flux-cored wire for submerged-arc welding. (Typ CrMo1V, 1.7745)																		
APPLICATIONS	CEWELD® SACW CrMo1V is a basic cored wire with Excellent weld puddle manipulation. Low spatter loss, easy slag removal. Extremely crack resistant. Suitable for economic welding of CrMoV-steels up to 550 °C. With Flux CEWELD FL155																		
PROPRIÉTÉS	Foundries, production welding																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.23: G (~EB2V)</td> </tr> <tr> <td>EN ISO</td> <td>24598-A: ST G (~CrMo1V)</td> </tr> <tr> <td>W.Nr.</td> <td>~1.7745</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>4</td> </tr> </table>	AWS	A 5.23: G (~EB2V)	EN ISO	24598-A: ST G (~CrMo1V)	W.Nr.	~1.7745	F-nr	6	FM	4								
AWS	A 5.23: G (~EB2V)																		
EN ISO	24598-A: ST G (~CrMo1V)																		
W.Nr.	~1.7745																		
F-nr	6																		
FM	4																		
CONVIENT POUR	<p>Typ 1Cr0,5Mo,V ISO 15608: ~5,1</p> <p>1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4, G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12</p>																		
AGRÉMENTS																			
POSITIONS DE SOUDAGE	<div style="display: flex; gap: 10px;">   </div>																		
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>V</th> </tr> </thead> <tbody> <tr> <td>0.12</td> <td>0.25</td> <td>0.85</td> <td>0.02</td> <td>0.02</td> <td>1.25</td> <td>0.3</td> <td>1.1</td> <td>0.25</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	V	0.12	0.25	0.85	0.02	0.02	1.25	0.3	1.1	0.25
C	Si	Mn	P	S	Cr	Ni	Mo	V											
0.12	0.25	0.85	0.02	0.02	1.25	0.3	1.1	0.25											
PROPRIÉTÉS MÉCANIQUES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{PO,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>690°C±15°C 6h</td> <td>550</td> <td>700</td> <td>20</td> <td colspan="2">70</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{PO,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		690°C±15°C 6h	550	700	20	70		HRc		
Heat Treatment	R _{PO,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness								
		RT																	
690°C±15°C 6h	550	700	20	70		HRc													
ETUVAGE	Not required																		
GAS ACC. EN ISO 14175																			