


# CEWELD AlMg 3 Tig

TYPE	TIG filler metal for welding Aluminium Magnesium alloys.										
TOEPASSINGEN	Suitable for base metals with maximum 3% Mg. These alloys are suitable for a big range of applications in the construction sector, in general, and in the structural industry. Widely used in ship and vessel building.										
EIGENSCHAPPEN	This alloy offers excellent weldability when properly cleaned prior to welding. Heavy parts and thicker plates should be preheated (150°C), prior to welding. The alloy shows good corrosion-resistance and an excellent colour-uniformity after anodizing. CEWELD® AlMg3 Tig offers also good resistance against seawater.										
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.10: ER5754</td> </tr> <tr> <td>EN ISO</td> <td>18273: S Al 5754 (AlMg3)</td> </tr> <tr> <td>F-nr</td> <td>22</td> </tr> </table>	AWS	A 5.10: ER5754	EN ISO	18273: S Al 5754 (AlMg3)	F-nr	22				
AWS	A 5.10: ER5754										
EN ISO	18273: S Al 5754 (AlMg3)										
F-nr	22										
GESCHIKT VOOR	Aluminium alloys: AlMg Mn, AlMg 3Mn, AlMg1, AlMg2, AlMg2,7Mn, AlMg3, AlMg3,5, AlMgSi0,5, AlMgSi0,8, G-AlMg3Si, 3.3315, 3.3535, 3.3206, 3.3541, EN AW 5005A, EN AW 5754, EN AW 6060, EN AC 51100, EN AW 5454, EN AW 5251										
GOEDKEURINGEN	CE										
LASPOSITIES											
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 50%; text-align: center;">Al</th> <th style="width: 50%; text-align: center;">Mg</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">Rem.</td> <td style="text-align: center;">3.2</td> </tr> </tbody> </table>	Al	Mg	Rem.	3.2						
Al	Mg										
Rem.	3.2										
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 20%;">Heat Treatment</th> <th style="width: 15%;">R<sub>P0,2</sub> (MPa)</th> <th style="width: 15%;">R<sub>m</sub> (MPa)</th> <th style="width: 10%;">A<sub>5</sub> (%)</th> <th style="width: 40%;">Hardness</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">As Welded</td> <td style="text-align: center;">80</td> <td style="text-align: center;">190</td> <td style="text-align: center;">20</td> <td style="text-align: center;">HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded	80	190	20	HRc
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness							
As Welded	80	190	20	HRc							
HERDROGEN	Not required										
GAS ACC. EN ISO 14175	I1, I3										



# CEWELD ALMg 3 Tig

ALMG 3 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407313
ALMG 3 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407320
ALMG 3 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407337
ALMG 3 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407344
ALMG 3 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407351
ALMG 3 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407368
ALMG 3 TIG 5,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407375