



CEWELD SAS 550-VW

TYPE	Sintered hardfacing strip for rebuilding and overlay applications.						
TOEPASSINGEN	Rebuilding wornout parts such as screws, chrusher hammers, drive tumblers, chrusher rolls, dredging parts etc...						
EIGENSCHAPPEN	The weld deposit offers excellent wear resistance against shocks and abrasion as well. Already the first layer gives excellent results even on mild steel due to the low dilution of the electro slag process. Due to the low dilution with the base metal a hardness exceeding 50 HRc can be achieved already in the first layer. Multiple layers can be applied to obtain full hardness at the final layer. Flux to be used FL 830 ESH						
CLASSIFICATIE	EN ISO		14700: C Fe8				
GESCHIKT VOOR	52-58 HRc electro slag and / or submerged arc strip for hardfacing against schock and wear, Rebuilding wornout parts such as screws, chrusher hammers, drive tumblers, chrusher rolls, dredging parts etc.. For ESW welding FL 830 ESHC should be used as welding flux to obtain the results mentioned in this datasheet.						
GOEDKEURINGEN							
LASPOSITIES							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Mn	Cr	Ni	Mo	V	W
	0.33	2.8	7	0.25	1.7	0.25	1.8
MECHANISCHE WAARDEN	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness	
	As Welded					56 HRc	
HERDROGEN	Not required						
GAS ACC. EN ISO 14175							