



CEWELD ER 70S-B2L Tig

TYPE	Low alloyed welding wire for high tensile strength and creep resistant steels						
TOEPASSINGEN	CEWELD ER70S-B2L is a low carbon content variation of the ER80S-B2 and is designed for the welding of 1¼Cr/½ Mo steel that require a lower as-welded hardness						
EIGENSCHAPPEN	This low carbon version of the B2 type is preferred where as welded repairs are done or where PWHT is not viable						
CLASSIFICATIE	AWS	A 5.28: ER 70S-B2L					
	EN ISO	21952-B: W 1CML					
	F-nr	6					
	FM	3					
GESCHIKT VOOR	For similar 1.25%Cr-0.5%Mo-alloyed, heat-resistant, ferritic steels. 1.7335, 1.7242, 1.7337, 1.7357 13CrMo 4-5, 13CrMo 4-4, 16 CrMo4, 16CrMo 4-4, GS-17CrMo 5-5, G17CrMo5-5 ASTM: A182 grades F11/F12, A199/A200 T11, A217 grades,WC6/WC11, A234 grades WP11/WP12, A335 grades P11/P12, A387 grades 11/12 BSI/AFNOR: K12073, K11598, K 11568, J 12073, J 12072, J 11872, K11564						
GOEDKEURINGEN	CE						
LASPOSITIES	      						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Mo
	0.04	0.45	0.55	0.015	0.015	1.3	0.6
MECHANISCHE WAARDEN	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness	
	620°C±15°C 1h		420	550	20	HRc	
HERDROGEN	Not required						
GAS ACC. EN ISO 14175	I1						



CEWELD ER 70S-B2L Tig

ER 70S-B2L TIG 1,6MM

Packaging	KG/unit	EanCode
Tube	5	8720663417473

ER 70S-B2L TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417503