




CEWELD MA 500

TYPE	Solid welding wire for rebuilding and hardfacing.				
TOEPASSINGEN	Rebuilding parts that are subject to abrasion combined with heavy impact.				
EIGENSCHAPPEN	Weld deposit with high carbon content offering excellent weldability.				
CLASSIFICATIE	EN ISO	14700: S Fe2			
	W.Nr.	1.8425			
GESCHIKT VOOR	Crushers, bucket teeth, hammers, crushers, pressure blocks etc.				
GOEDKEURINGEN	CE				
LASPOSITIES	PAPBPCPDPEPF				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Al
	1.1	0.4	1.9	1.8	0.1
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded				50 HRc
HERDROGEN	Not required				
GAS ACC. EN ISO 14175	M21				



CEWELD MA 500

MA 500 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403087