



CEWELD E DUR 400 KB

TYPE	Basic coated electrode for rebuilding machine parts and buffer layers.		
TOEPASSINGEN	Hardfacing, rebuilding, overlays, machine parts, wheels, buffer layers, etc.		
EIGENSCHAPPEN	Outstanding alloy against high impact combined with abrasion including metal to metal friction. The weld deposit of Dur E 400Kb is an exceptional easy to apply alloy without any risk for cracks and can also be applied on austenitic manganese steels. The weld deposit is machinable with tungsten tool tips. Very good weld deposit appearance and outstanding welding properties on both AC and DC+. Preheating is not required.		
CLASSIFICATIE	EN ISO DIN	14700: E Fe1 8555: E 1-UM-400-P	
GESCHIKT VOOR	Rebuilding worn machine parts, Stone crushers, Hammers, Gears, Cams etc.		

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Mn	Cr	Fe
0.1	0.85	3	Rem.

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				400 HB

HERDROGEN 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E DUR 400 KB

E DUR 400 KB 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663401618

E DUR 400 KB 4,0 X 450MM

Packaging	KG/unit	EanCode
Can	3,2	8720663401625