



CEWELD FL 160

TYPE	High basic SAW flux with low hydrogen content.
TOEPASSINGEN	Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..
EIGENSCHAPPEN	FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20
CLASSIFICATIE	EN ISO 14174: SA FB 1 55 AC H5
GESCHIKT VOOR	S355, S420, S460, X65, X70, X80

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

Al ₂ O ₃	CaF ₂	SiO ₂	CaO+MgO
20	20	15	40

MECHANISCHE WAARDEN

HERDROGEN Not required

GAS ACC. EN ISO 14175



CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015