



CEWELD SA Nicro 600 strip

TYPE Nickel Chromium solid strip

TOEPASSINGEN This strip is suitable for both electroslag (ESW) and sub arc (SAW) process. Typical applications include cladding of vessels for the petrochemical, refinery and chemical industries

EIGENSCHAPPEN Weld metal deposited by SA Nicro 600 has high strength and good corrosion resistance, including oxidation resistance and creep-rupture strength at elevated temperatures. Use FL 860 ESHC flux

CLASSIFICATIE
AWS A 5.14: EQNiCr-3
EN ISO 18274: B Ni 6082 (NiCr20Mn3Nb)
W.Nr. 2.4806

GESCHIKT VOOR SA Nicro 600 is mainly used for ESW and SAW cladding of carbon steel to obtain corrosion and creep resistant layers. Go to [FL 860 ESHC](#) suitable flux
E Ni 6182 (Ni Cr 15 Fe6Mn), E NiCrFe-3
2.4630, 2.4631, 2.4669, 2.4816, 2.4817, 2.4851, 2.4867, 2.4870, 2.4951 ... (1.4816, 1.4864, 1.4876, 1.4583, 1.4886, 1.5637, 1.5662, 1.5680, 1.6900, 1.6901, 1.6903, 1.6906)
NiCr20Ti, NiCr21TiAl, NiCr15Fe7TiAl, NiCr15Fe, LC-NiCr15Fe, NiCr23Fe, NiCr60 15, NiCr80 20, NiCr 10, NiCr20Ti 1.5637 12 Ni 14, X8Ni9, 12Ni19, X12CrNi18 9, GX8CrNi18 10, X10CrNiTi18 10, X5CrNi18 10
UNS Nr: K81340 - N06600 - N06601 - N08800 - N08810
ASTM B163, B166, B167 und B168
Alloy 600, Alloy 600 L, Alloy 800 / 800H UNS N06600, N07080, N0800, N0810

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Nb	Ti	Fe
0.08	0.4	3	0.02	0.01	21	75	2.8	0.2	2

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	390	650	37	HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175