



CEWELD Alloy X Tig

TYPE	CEWELD Alloy X is a nickel- chromium-iron-molybdenum alloy wire rod								
TOEPASSINGEN	CEWELD Alloy X Tig is a nickel- chromium-iron-molybdenum alloy that possesses an exceptional combination of oxidation resistance, fabricability and high-temperature strength. It has also been found to be exceptionally resistant to stress-corrosion cracking in petrochemical applications.								
EIGENSCHAPPEN	CEWELD Alloy X Tig exhibits good ductility after prolonged exposure at temperatures of 1200, 1400, 1600°F (650, 760 and 870°C) for 16,000 hours. Suitable for joining and cladding Nickel alloys, stainless steel, carbon steel and low alloyed steels. UNS: N06002								
CLASSIFICATIE	AWS	A 5.14: ERNiCrMo-2							
	EN ISO	18274: S Ni 6002(NiCr21Fe18Mo9)							
	W.Nr.	2.4665							
	F-nr	43							
	FM	6							
GESCHIKT VOOR	2.4665 UNS: N06002 Alloy HX, X, AMS 5754, AMS 5798, ASTM B619, Nickel alloys, stainless steel, carbon steel and low alloyed steels.								
GOEDKEURINGEN									
LASPOSITIES	PAPBPCPDPEPFPG								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Mo	Fe	W	Co
	0.1	0.8	0.8	22	55	9	19	0.8	2
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness	
					RT				
	As Welded		660	30	100			HRc	
HERDROGEN	Not required								
GAS ACC. EN ISO 14175	I1								



CEWELD Alloy X Tig

ALLOY X TIG 0,8 X 914MM

Packaging	KG/unit	EanCode
Tube	0,91	8720663420299

ALLOY X TIG 1,14 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663420312

ALLOY X TIG 1,6 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663420329

ALLOY X TIG 2,4 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663420336