



CEWELD NiCro 601

TYPE	Nickel-Chromium-Aluminum alloy for Mig welding alloy 601.						
TOEPASSINGEN	CEWELD NiCro 601 is used for severe applications where the exposure temperature can exceed 1150°C (2100°F).						
EIGENSCHAPPEN	Excellent resistance against corrosion and oxidation and suitable for applications when exposed to hydrogen sulfide or sulfur dioxide.						
CLASSIFICATIE	AWS	A 5.14: ER NiCrFe-11					
	EN ISO	18274: S Ni 6601(NiCr23Fe15Al)					
	F-nr	43					
	FM	6					
GESCHIKT VOOR	The nominal composition (wt.-%) of filler metal of this classification is 61 Ni, 23 Cr, 14 Fe, and 1.4 Al. Filler metal of this classification is used for welding nickel-chromium-iron-aluminum alloy (ASTM B 166, B 167, and B 168 having UNS number N06601) to itself and to other high-temperature compositions.						
GOEDKEURINGEN							
LASPOSITIES							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Fe	Al
	0.04	0.24	0.53	22.8	61	13.35	1.4
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT		
	As Welded	648	700	42	60		HRc
HERDROGEN	Not required						
GAS ACC. EN ISO 14175	I1						



CEWELD NiCro 601

NICRO 601 1,14MM

Packaging	KG/unit	EanCode
BS-300	15	8720663418296