



CEWELD CuSn

TYPE Copper welding wire alloyed with Sn for Mig and Tig welding

TOEPASSINGEN Boilers and tubes out of copper or copper alloys, oven soldering etc..

EIGENSCHAPPEN

- High quality alloyed copper wire
- Sound, pore free deposits and good electrical conductivity
- Excellent corrosion resistance

CLASSIFICATIE

AWS	A 5.7: ERCu
EN ISO	24373: Cu 1898 / CuSn1
W.Nr.	~2.1006
F-nr	31

GESCHIKT VOOR Bronze alloy with minimally 0.8 tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Cu and copper- alloys. Widely used in oven soldering.

2.0040 - OF-Cu,
2.0070 - SE-Cu,
2.0076 - SW-Cu,
2.0090 - SF-Cu

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


Si	Mn	Cu	Sn
0.3	0.3	98.5	0.8

MECHANISCHE WAARDEN

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		220		60 HB

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD CuSn

CUSN 0,8MM	Packaging	KG/unit	EanCode
	D-300	15	8720663408624

CUSN 1,0MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408631

CUSN 1,2MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408648
	Drum	250	8720682051528

CUSN 1,6MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408655