

CEWELD ER 90S (P24) Tig

TYPE	Tig welding wire for creep resistant P/T 24 type of steels.	
TOEPASSINGEN	The alloy finds use for waterwalls in ultra-super-critical (USC) boilers in the power generating industry.	
EIGENSCHAPPEN	TIG/GTAW rod for T24 creep resistant steel. The T24 alloy is a modified 2.25%Cr1%Mo alloy with additions of Nb and V to improve high temperature creep performance. Interpass temperature: max. 300°C	
CLASSIFICATIE	AWS	A 5.28: ER 90S-G
	EN ISO	21952-A: W ZCrMo2VNb
	F-nr	6
	FM	3
GESCHIKT VOOR	alloy 24, 2.5%Cr1%Mo modified, creep resisting ferritic steels. X7CrMoVTiB 10-10 1.7378 / 7CrWVMoNb9-6 - 1.8201 ASTM: A/SA 335 Grade P24 - A/SA 213 Grade T24 A/SA 335 Grade P23 - A/SA 213 Grade T23	

GOEDKEURINGEN CE

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Mo	V	Nb
0.1	0.25	0.9	0.01	0.01	2.3	1	0.3	0.02

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT		
730°C- 760°C 1h	650	750	20	50		HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1

CEWELD ER 90S (P24) Tig

ER 90S (P24) TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720682051702