



CEWELD Alloy B3 Tig

TYPE	Nickel based wire or rod for welding Hastelloy B2 and B3										
TOEPASSINGEN	Plants for the production and processing of hydrochloric, sulfuric, acetic and phosphoric acids. Plants for ethylbenzene production. Pressure vessels for chloroprene production. Plants for the production of phenol from isopropyl benzene. Pyrolysis plants for the production of acetic anhydride										
EIGENSCHAPPEN	CEWELD® Alloy B3 Tig is a nickel-base alloy with excellent resistance tot hydrochlorid acid at all concentrations and tempertures. It also withstands hydrogen chloride, sulfuric, acetic, hydrofluoric nd phosphoric acids. The alloy has improved thermal stability, fabricability and stress corrosion cracking resistance.										
CLASSIFICATIE	AWS	A 5.14: ERNiMo-10									
	EN ISO	18274: S Ni 1067(NiMo30Cr)									
	W.Nr.	2.4695									
	F-nr	43									
	FM	6									
GESCHIKT VOOR	Hastelloy B2, Hastelloy B3 oder B4, Nicrofer® 6629 NiMo29Cr, NiMo28 2.4600, 2.4617 UNS N 10629, N 10629, N10665 ASTM: B 333, B 335, B 564, B 619, B 622, B 626										
GOEDKEURINGEN											
LASPOSITIES											
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Ni	Mo	Ti	V	Fe	W	Co
	0.001	0.08	0.59	1.54	67.2	28.6	0.05	0.008	1.44	0.5	0.3
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V					Hardness	
	As Welded	540	820	45	RT					195	
										HRc	
HERDROGEN	Not required										
GAS ACC. EN ISO 14175	I1										